

# **ORAJET® Series 3675 Perforated Window Graphics PVC Digital Media (50/50)**

## **Description**

5.5-mil, perforated calendered PVC film available in white with a gloss finish and black backing. 50% printable area.

## **Release Paper**

83# silicone coated paper

## **Adhesive**

Clear, solvent-based, permanent adhesive

## **Applications**

For short to medium-term window graphics applications.

## **Technical Data**

<b>Thickness</b> (without protective paper and adhesive)	5.5 mil	
<b>Dimensional Stability</b> (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, < 0.016"	
<b>Temperature Resistance</b>	Adhered to aluminum, -40°F to +176°F, no variation	
<b>Fire Behavior</b> (DIN 75200)	Adhered to steel, self-extinguishing	
<b>Fire Rating</b>	ASTM E 84-07 Class "A"	
<b>Adhesive Power</b> (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 2.74 lb/in	
<b>Tensile Strength</b> (DIN EN ISO 527)		
Along	Min. 5 MPa	
Across	Min. 5 MPa	
<b>Elongation at Break</b> (DIN EN ISO 527)		
Along	Min. 50%	
Across	Min. 50%	
<b>Seawaterability</b> (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation	
<b>Shelf Life</b> (68°F/50% relative humidity)	2 years	
<b>Minimum Application Temperature</b>	50°F	
<b>Available Lengths</b>	150' (50-yard)	30' (10-yard)
<b>Available Widths</b> (inches)	24, 30, 54	24, 30, 54
<b>Minimum Life Expectancy</b> (based on accepted application procedures on vertical surfaces)	3 years (Unprinted)	
<b>Recommended Laminate</b>	ORAGUARD® Series 297F	

Oracal recommends that printed film is allowed to dry for at least 24 hours at 70°F (48-72 preferred) before applying a laminate.

## **Attention**

Recycling Recommendation: Waste class similar to household waste, is to be recycled according to the local regulations.

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.

**For instant access to more information click on the links below**

## **Profiles**

<http://www.oracal.com/knowledge/icc-profiles.asp>

## **Tech Support**

<http://www.oracal.com/knowledge/contact-support.asp>

## **Find a Distributor**

<http://www.oracal.com/distributors/>

## **General Warranty**

[http://www.oracal.com/\\_userfiles/File/GeneralWarranty.pdf](http://www.oracal.com/_userfiles/File/GeneralWarranty.pdf)

